

POWDER HIGH SPEED TOOL STEEL

Daido Brand	Nearest Equivalent			Chemical Composition									Delivery Conditioned Annealed	Hardening Temperature (°C)	Quench	As Temepred Hardeness (HRC)						Application
	JIS	AISI	DIN	C	Si	Mn	Ni	Cr	Mo	W	V	Other				200°C	300°C	400°C	500°C	550°C	600°C	
POWDER HIGH SPEED TOOL STEEL																						
DEX20				1,30				4,00	5,00	6,50	3,00		Max 285	1100 - 1180	Oil, Salt				64	67	62	Fine Blanking Press Die, Punch for Stainless Steel, etc
DEX40				1,30				4,00	5,00	6,50	3,00	Co 8.0	Max 285	1130 - 1220	Oil, Salt				66	67	64	Fine Blanking Press Die, Punch for Stainless Steel, etc